

TEXTUROL 7970

(weft)



DESCRIPTION

Fluid, mineral based oil. Self-emulsifiable in water.

APPLICATIONS

Fibre lubricant for weft yarns. Suitable for application to dyed and undyed yarns intended for weaving.

APPLICATION DETAILS

Suitable for application by roller and trough or other methods. TEXTUROL 7970 is also suitable for application during cone winding. When applied by lick roller, it is recommended that the rollers should rotate in the same direction as the yarn travel. Suggested amount to apply: Yarns - 1% to 3% oil on the weight of the fibre is recommended.

PERFORMANCE DATA

- Provides a reduction in fibre / fibre and fibre / metal frictional properties, promoting smooth and even running of the yarn in weaving.
- Provides good anti-static properties to the yarns when used at the recommended application levels.
- TEXTUROL 7970 is designed to give a significant reduction in oil splashing during application by either lick roller or other system. Benefits therefore include reduced oil wastage, cleaner machinery and reduced risk of oil dripping, and a cleaner and less hazardous working environment. The oil is not shear sensitive and the anti-splash properties are not affected by pumping the oil.
- TEXTUROL 7970 is readily taken up onto the yarn when applied by either lick roller or other systems, and therefore reduced roller speeds may be used, and improved evenness of oil application achieved.
- The oil has good resistance to oxidation and yellowing.
- The oil is non-corrosive to the metals commonly used in textile machinery.

SCOURING SUGGESTIONS

A pre-scour or pre-rinse is normally advisable prior to fabric dyeing. The oil is readily removed from fabrics using mild aqueous scouring systems. A scour incorporating non-ionic detergent and alkali is recommended, at a liquor temperature not exceeding 60°C. When processing polyester fabrics in jet dyeing machinery a simple water only rinse at 20°C before dyeing is normally sufficient.

NOTES

Oil-feed systems - we strongly recommend that the use of zinc galvanized or copper pipework is avoided for oil distribution systems. Stainless steel, or in some cases mild steel, are suitable materials.

BENJ^M R. VICKERS & SONS LTD.

Registered Office
6 Clarence Road, Leeds,
LS10 1ND, United Kingdom

Registered in England
Company No. 00130013

Tel: +44 (0) 113 386 7654
Web: www.vickers-oil.com
Email: inbox@vickers-oil.com

Follow us on   

Certified to the ISO 9001
Quality Standard and the
ISO 14001 Environmental
Management Standard



FM 01851 EMS 40717

TEXTUROL 7970 (weft)



HANDLING AND STORAGE

Store above 5° C. Warm before use.

TYPICAL CHARACTERISTICS AND PROPERTIES

TEXTUROL 7970	UNITS	TYPICAL RESULT
Colour		Clear pale yellow
Viscosity @ 21°C	cSt	Approx. 24
Density @ 15°C	kg/l	Approx. 0.86
Cloud Point	°C	< 0
Flash Point (SETA)	°C	> 130
Ionic Character		Non-ionic
Emulsifiability		Self-emulsifiable in water
Shelf Life		7 years in original container stored out of direct sunlight

Vickers Oils, its officers, employees and agents assume no responsibility and shall not be liable to any person for any loss, damage or expense caused by reliance on the information or advice in this document or howsoever provided, unless that person has signed a contract with Vickers Oils for the provision of this information or advice and in that case responsibility or liability is exclusively on the terms and conditions set out in that contract. Products should only be used for the applications specified. The supplier cannot accept responsibility if they are used in any other applications.

BENJ[®] R. VICKERS & SONS LTD.

Registered Office
6 Clarence Road, Leeds,
LS10 1ND, United Kingdom

Registered in England
Company No. 00130013

Tel: +44 (0) 113 386 7654
Web: www.vickers-oil.com
Email: inbox@vickers-oil.com

Follow us on   

Certified to the ISO 9001
Quality Standard and the
ISO 14001 Environmental
Management Standard



FM 01851 EMS 40717