

VICKERLUBE HD EP2



PART NUMBER

25271

DESCRIPTION

VICKERLUBE HD EP2 is a heavy duty, lithium complex, extreme pressure grease, formulated from mineral base oils and selected additives. The EP additives make it particularly suitable for use in severe applications typically encountered in mining, quarrying, cement and other heavy industries.

APPLICATIONS

It is designed for use in equipment demanding an extreme pressure NLGI 2 grease. Typically used in plain and anti-friction bearings, pins and bushings and sliding surfaces.

CERTIFICATION

VICKERLUBE HD EP2 is manufactured to ISO 9001:2015 and ISO 14001:2015.

FEATURES AND BENEFITS

- | | |
|-------------------------------|---|
| • Extreme pressure properties | Excellent load carrying, protection against shock loads |
| • Low water washout | Increases relubrication intervals |
| • Oxidation resistant | Increased fluid life |
| • Corrosion inhibited | Protects parts against corrosion |

METHOD OF APPLICATION

VICKERLUBE HD EP2 can be applied manually or via a central lubrication system designed for NLGI 2 greases.

BENJ^N R. VICKERS & SONS LTD.

Registered Office

6 Clarence Road, Leeds,
LS10 1ND, United Kingdom

Registered in England

Company No. 00130013

Tel: +44 (0) 113 386 7654
Fax: +44 (0) 113 386 7676
Web: www.vickers-oil.com
Email: inbox@vickers-oil.com

Certified to the ISO 9001
Quality Standard and the
ISO 14001 Environmental
Management Standard



FM 01851 EMS 40717

VICKERLUBE HD EP2



TYPICAL CHARACTERISTICS AND PROPERTIES

VICKERLUBE HD EP2	TEST METHOD	RESULT
Appearance	Visual	Red
Consistency	ASTM D217	NLGI 2
Base Oil Viscosity at 40°C (cSt)	ASTM D7042	175
Penetration, worked	ASTM D217	293
Dropping Point (°C)	ASTM D2265	272
Water Washout at 79°C (%)	ASTM D1264	1.4
Water Resistance, 90°C	DIN 51807-1	1-90
Copper Corrosion	ASTM D4048	1b
EMCOR, deionised water	ASTM D6138	0,0
4-ball weld load (kg)	ASTM D2596	>315
4-ball wear test (mm)	ASTM D2266	0.5
Timken OK Load (lbs)	ASTM D2509	40
Shelf Life		3 years in original sealed containers whilst stored out of direct sunlight

Vickers Oils, its officers, employees and agents assume no responsibility and shall not be liable to any person for any loss, damage or expense caused by reliance on the information or advice in this document or howsoever provided, unless that person has signed a contract with Vickers Oils for the provision of this information or advice and in that case responsibility or liability is exclusively on the terms and conditions set out in that contract. Products should only be used for the applications specified. The supplier cannot accept responsibility if used in any other applications.

BENJ^N R. VICKERS & SONS LTD.

Registered Office
6 Clarence Road, Leeds,
LS10 1ND, United Kingdom
Registered in England
Company No. 00130013

Tel: +44 (0) 113 386 7654
Fax: +44 (0) 113 386 7676
Web: www.vickers-oil.com
Email: inbox@vickers-oil.com

Certified to the ISO 9001
Quality Standard and the
ISO 14001 Environmental
Management Standard



FM 01851 EMS 40717